

Received: 17 February, 2021

Accepted: 22 March, 2021

Published: 23 March, 2021

***Corresponding authors:** Chao Wang, Department of Mechanical Engineering, the University of Texas at Dallas, Richardson, TX, 75080, USA,
E-mail: wang.chao@utdallas.edu

Xiaozhou Cao, School of Metallurgy, Northeastern University, Shenyang, Liaoning, 110819, China,
E-mail: caoxz@smm.neu.edu.cn

Xiangxin Xue, School of Metallurgy, Northeastern University, Shenyang, Liaoning, 110819, China,
E-mail: xuexx@mail.neu.edu.cn

Keywords: AlB_{12} ; SHS; Theoretical calculations; Adiabatic temperature; Standard gibbs free energy

<https://www.peertechzpublications.com>



Check for updates

Review Article

Theoretical calculation of self-propagating high-temperature synthesis (SHS) preparation of AlB_{12}

Chao Wang^{1*}, Xiaoming Cao², Mengge Dong³, Lu Zhang⁴, Jianxing Liu³, Xiaozhou Cao^{3*} and Xiangxin Xue^{3*}

¹Department of Mechanical Engineering, the University of Texas at Dallas, Richardson, TX, 75080, USA

²Institute of Metal Research, Chinese Academy of Science, Shenyang, Liaoning, 110016, China

³School of Metallurgy, Northeastern University, Shenyang, Liaoning, 110819, China

⁴School of Energy and Environment, Anhui University of Technology, Ma'anshan, 243002, China

Abstract

Although experimental results of preparing AlB_{12} by self-propagating high-temperature synthesis using $Mg-B_2O_3-Al_2O_3$ as raw material has been studied, the theoretical calculations for the preparation of AlB_{12} have not been examined as thoroughly. In this article, for the first time, we report on the study of theoretical calculation and the adiabatic temperature, calculated, and compared with the actual reaction temperature. The Gibbs free energy for each level of reaction is also calculated. The calculation results show that the adiabatic temperature is 2789.5 K, the standard Gibbs free energy of each reaction is less than 0, and the reaction can proceed spontaneously, which is consistent with the results of the experiment.

Introduction

In the process of SHS synthesis reaction research, the reaction system must meet certain thermodynamic conditions so that the reaction can self-sustain the combustion reaction process [1-3]. Among them, the most basic thermodynamic parameter is the Adiabatic Temperature of the reaction [4-7]. Self-propagating high-temperature synthesis (or SHS) is a chemical reaction under special conditions [8-11]. Thermodynamic analysis mainly discusses the feasibility of the reaction, such as how to judge whether a chemical reaction can proceed under given conditions, to what extent, and what effect the reaction will have after changing the conditions [12-14].

Thermodynamic analysis of the combustion system is the basis for studying the SHS process [15-17]. The main task of thermodynamic analysis is to calculate the combustion temperature and product balance under adiabatic conditions,

that is, when all the heat released by the reaction is used to heat the product synthesized during the reaction [18,19]. The calculation is based on the minimum principles of conservation of mass and energy and chemical potential (Gibbs free energy) [20,21]. Thermodynamic calculation is a very effective method for studying the SHS process, as it helps to control the temperature and composition of the process products [22-25].

Previous studies have shown that AlB_{12} can be prepared by the self-propagating method [26-28] and the reaction temperature is higher than 2300°C. However, the self-propagating reaction has not been calculated theoretically. In this article, the basic principle of self-propagating reaction is explained, the theoretical calculation of self-propagating preparation of AlB_{12} is studied, and the calculated results are compared with the actual test results.


Principle of self-propagating reaction

Adiabatic temperature is an important thermodynamic



parameter describing the characteristics of combustion synthesis (SHS) reaction. Merzhanov et al. put forward the following empirical criterion, that is, only when $T_{ad} > 1800K$, the SHS response can be self-sustained [25]. Munir found that the ratio of the heat of formation of some compounds below their melting point to the heat capacity at 298K has a linear relationship with $\Delta H_{298}^{\theta} / \Delta Cp_{298}$ and T_{ad} [29,30]. It can be concluded that the reaction can maintain itself only when $\Delta H_{298}^{\theta} / \Delta Cp_{298} \geq 2000K$ (corresponding to $T_{ad} \geq 1800K$). Otherwise, only the outside world can supplement energy into the system, such as by using a "preheating", "chemical furnace" or the use of "thermal explosion" methods to maintain self-reaction.

The self-propagating reaction can be expressed as equation (1):



(1) Taking the enthalpy of the system as the state function, the heat released during the reaction is:

$$\Delta H = \Delta H_{298}^{\theta} = \int_{298}^{T_{ad}} \Delta Cp dT \quad (2)$$

in which ΔH_{298}^{θ} is the standard enthalpy for formation of the product at a temperature of 298K, and ΔCp is the heat capacity of the product.

When adiabatic, the thermal effect of the system is $\Delta H = 0$, and the adiabatic temperature T_{ad} can be calculated in the following situations: When $T_{ad} < T_{mp}$:

$$-\Delta H_{298}^{\theta} = \int_{298}^{T_{ad}} \Delta Cp dT \quad (3)$$

when $T_{ad} = T_{mp}$:

$$-\Delta H_{298}^{\theta} = \int_{298}^{T_{ad}} \Delta Cp dT + \gamma \Delta H_m \quad (4)$$

in which ΔH_{298}^{θ} is the enthalpy of the product in the molten state, and ΔCp_{298} is the heat of fusion of the product.

when $T_{ad} > T_{mp}$:

$$-\Delta H_{298}^{\theta} = \frac{1}{n} \int_{298}^{T_{ad}} \Delta Cp dT + \Delta H_m + \int_{T_{mp}}^{T_{ad}} \Delta Cp dT \quad (5)$$

It can be calculated approximately with the following equation:


$$Cp = a + b \times 10^{-3} \times T + c \times 10^5 T^{-2} + d \times 10^{-6} T^2 \quad (6)$$

Calculation of gibbs free energy

The Gibbs free energy change ΔG is a criterion for determining whether a chemical can proceed spontaneously under constant temperature and pressure conditions [31]. The Gibbs free energy in the standard state can roughly reflect the possibility of a reaction or reaction trend. If $\Delta G^{\theta} < 0$ in the system, the reaction process is irreversible and proceeds

spontaneously. If it is $\Delta G^{\theta} = 0$, the reaction process is reversible and spontaneous. And if it is $\Delta G^{\theta} > 0$, the reaction cannot proceed spontaneously.

The self-propagating reaction system can be expressed as equation 7 as:



In equation (7), V_i is the measurement coefficient of the element or compound B_i .

The calculation equation for the change of its standard free energy is:

$$\Delta G^{\theta} = \sum v_i G_i T \quad (8)$$

In the equation (8), G_i , T is the free energy of the element or compound B at temperature T .

In the Al_2O_3 - B_2O_3 -Mg system, the following chemical reactions generally occur:




Table 1 shows the free energy changes. A more systematic study of the thermodynamics of related reaction systems, prediction of the phases that may exist and appear in the reactants and products from the perspective of thermodynamics, provides a theoretical basis for the regulation of the self-propagating high-temperature synthesis process.

Result of calculation

The adiabatic temperature was calculated using HSC6.0 software, and the adiabatic temperature of the reactions is 2789.5 K. Previous studies have shown that the reaction temperature of self-propagating preparation of AlB_{12} exceeds 2300°C (2573 K). This tested result matches the calculation

Table 1: The relation between free energy and temperature of different reactions.

Equation	$\Delta G^{\theta} = A + BT$ (kJ/mol)	Temperature range/K
$Al_2O_3 + 3Mg \rightarrow 2Al + 3MgO$	-128.01584+0.00792T	273-893
	-139.08535+0.01888T	893-2303
$B_2O_3 + 3Mg \rightarrow 2B + 3MgO$	-262.37839+0.07233T	2303-2573
	-532.60705+0.05814T	273-723
$Al + 12B \rightarrow AlB_{12}$	-559.15828+0.0947T	723-853
	-600.18482+0.13789T	853-2353
$Al_2O_3 + 12B_2O_3 + 39Mg \rightarrow 2AlB_{12} + 39MgO$	-505.72672+0.09833T	2353-2573
	-220+0.00745T	933-2473
	-825.48067+0.23708T	2473-2789.5
	-1219.78117+0.16076T	273-933
	-1707.37528+0.21488T	933-2573



result. Since $=2789.5 \text{ K} > 1800 \text{ K}$, self-propagation can proceed smoothly. Note that the reaction always has $\Delta G^0 < 0$ in Table 1, so the reaction can proceed spontaneously. Such calculation results can indicate that it is possible to prepare AlB_{12} by self-propagating reaction with Al_2O_3 , B_2O_3 , and Mg as raw materials, and the reaction temperature can support the completion of the propagation reaction.

Summary

The calculation results of preparing AlB_{12} using Mg, Al_2O_3 and B_2O_3 as the raw materials shows that the adiabatic temperature of the system is 2789.5K, which meets the self-propagating reaction conditions. The calculated results are consistent with the actual test results. The Standard Gibbs free energy of the reaction formula is less than zero, which also proves the possibility of self-propagating reactions.

Acknowledgements

This work was supported by Fundamental scientific research business expenses of central universities (award # N10060200).

References

1. Matkovich VI (1977) Boron and refractory borides.
2. Luo X, Wang Z, Hu X, Shi Z, Gao B, et al. (2009) Influence of metallic additives on densification behaviour of hot-pressed TiB_2 . *Light Metals* 1151-1155. [Link: https://bit.ly/3rcpwCl](https://bit.ly/3rcpwCl)
3. Shiriev AA, Mukasyan AS (2017) Thermodynamics of SHS Processes in Concise Encyclopedia of Self-Propagating High-Temperature Synthesis. (Elsevier, 2017) 385-387.
4. Tao W, Wang Z, Chen G, Shi Z, Gao B, et al. (2009) Finite element analysis of thermo-electric coupled field in 400kA large-scale aluminum reduction cell. in 2009 World Non-Grid-Connected Wind Power and Energy Conference (IEEE) 1-4. [Link: http://bit.ly/3f6DCU0](http://bit.ly/3f6DCU0)
5. Cao X, Wang C, Shi L, Yang H, Xue X, et al. (2013) Effect of Ni addition on pressureless sintering of tungsten diboride. *International Journal of Refractory Metals and Hard Materials* 41: 597-602. [Link: http://bit.ly/3lEdbWX](http://bit.ly/3lEdbWX)
6. Cao X, Wang HY, Meng X, Wang C, Yang H, et al. (2011) High temperature electrochemical synthesis of tungsten boride from molten salt. in *Advanced Materials Research (Trans Tech Publ)* 463-466. [Link: https://bit.ly/3cd7goM](https://bit.ly/3cd7goM)
7. Yukhvid V (1992) Modifications of SHS processes. *Pure and Applied Chemistry* 64: 977-988. [Link: http://bit.ly/397gQr8](http://bit.ly/397gQr8)
8. Wang C, Xue X, Cao X, Yang H (2012) Effect of BN Addition on Mechanical Properties and Microstructure of TiB_2 -Al Composites. *Journal of Northeastern University (Natural Science)* 19. [Link: https://bit.ly/3rajlr](https://bit.ly/3rajlr)
9. Chao W, Xiangxin X, Xiaozhou C, Lu Z, Jian Z, et al. (2013) A New Method of Fabricating AlN-TiB₂ Composite Ceramics. *Materials and Manufacturing Processes* 28: 953-956. [Link: https://bit.ly/3lKH0VF](https://bit.ly/3lKH0VF)
10. Wang C, Zhang J, Xue XX, Cao XZ (2013) Fabrication B-Ni-Al Shielding Materials by Vacuum Metal Infiltration. *Advanced Materials Research (Trans Tech Publ)* 641-642: 410-413. [Link: https://bit.ly/31aLvPP](https://bit.ly/31aLvPP)
11. Zhang P, Xia T, Zhang G, Yan L, Zhao W (2007) Thermodynamic analysis of Ti powder synthesized by SHS thermitreaction. *Transactions of Nonferrous Metals Society of China* 17: s27-s31. [Link: https://bit.ly/3tQStpH](https://bit.ly/3tQStpH)
12. Cao X, Xu L, Wang C, Li S, Dong W, et al. (2020) Electrochemical Behavior and Electrodeposition of Sn Coating from Choline Chloride-Urea Deep Eutectic Solvents. *Coatings* 10: 1154. [Link: https://bit.ly/316aNif](https://bit.ly/316aNif)
13. Yi HC, Moore J (1990) Self-propagating high-temperature (combustion) synthesis (SHS) of powder-compacted materials. *Journal of Materials Science* 25: 1159-1168. [Link: https://bit.ly/2QzEBBX](https://bit.ly/2QzEBBX)
14. Zhang W, Wang HY, Wang PJ, Zhang J, He L, et al. (2008) Effect of Cr content on the SHS reaction of Cr-Ti-C system. *Journal of Alloys and Compounds* 465: 127-131. [Link: http://bit.ly/2NH5Kl8](http://bit.ly/2NH5Kl8)
15. Cao X, Wang C, Xue X, Yang H (2014) Preparation of tungsten boride ceramic by pressureless sintering. *Journal of Inorganic Materials* 29: 498-502. [Link: http://bit.ly/3cUOVG](http://bit.ly/3cUOVG)
16. Cao X, Wang C, Xue X, Cheng G (2015) Effect of ti addition on the residual aluminium content and mechanical properties of the B₄C-al composites produced by vacuum infiltration. *Archives of Metallurgy and Materials* 60: 2493-2398. [Link: https://bit.ly/3rhkbtL](https://bit.ly/3rhkbtL)
17. Dong M, Xue X, Yang H, Liu D, Wang C, et al. (2016) A novel comprehensive utilization of vanadium slag: as gamma ray shielding material. *Journal of Hazardous Materials* 318: 751-757. [Link: http://bit.ly/397hvc0](http://bit.ly/397hvc0)
18. Xue X, Wang C, Tao J, Cao XZ, Ri R, et al. (2013) Research Progress on Aluminum-Boron Compounds (Al-B) and Its Composite Materials. *Bulletin of the Chinese Ceramic Society* 26. [Link: https://bit.ly/3161Gy5](https://bit.ly/3161Gy5)
19. Mamyán S (2002) Thermodynamic analysis of SHS processes. in *Key Engineering Materials (Trans Tech Publ)* 1-8.
20. Chao W, Xiangxin X, Xiaozhou C, He Y, Gongjin C (2013) The effect of Ti addition on the microstructure and fracture toughness of BN-Al composite materials synthesized by vacuum infiltration. *Archives of Metallurgy and Materials* 58: 509-512. [Link: https://bit.ly/3ccoXVb](https://bit.ly/3ccoXVb)
21. Shiryayev A, Nersesyan M, Ming Q, Luss D (1999) Thermodynamic feasibility of SHS of SOFC materials. *Journal of Materials Synthesis and Processing* 7: 83-90. [Link: https://bit.ly/3seMWZF](https://bit.ly/3seMWZF)
22. Qi D, Gao Y, Ren Z, Cao X, Wang C, et al. (2019) Preparation and Erosion Performance for Co-continuous Phase Composites of $\text{Si}_3\text{N}_4/1\text{Cr}18\text{Ni}9\text{Ti}$. *Chinese Journal of Materials Research* 33: 34-42. [Link: http://bit.ly/3rdpo6b](http://bit.ly/3rdpo6b)
23. Wang C, Hossain Bhuiyan ME, Moreno S, Minary-Jolandan M (2020) Direct-Write Printing Copper-Nickel (Cu/Ni) Alloy with Controlled Composition from a Single Electrolyte Using Co-Electrodeposition. *ACS Appl Mater Interfaces* 12: 18683-18691. [Link: http://bit.ly/2PeD9nl](http://bit.ly/2PeD9nl)
24. Mahmoudi M, Wang C, Moreno S, Burlison SR, Alatalo D, et al. (2020) Three-Dimensional Printing of Ceramics through "Carving" a Gel and "Filling in" the Precursor Polymer. *ACS Applied Materials & Interfaces* 12: 31984-31991. [Link: https://bit.ly/3d2iQC2](https://bit.ly/3d2iQC2)
25. Merzhanov A (1995) History and recent developments in SHS. *Ceramics International* 21: 371-379. [Link: http://bit.ly/3184E55](http://bit.ly/3184E55)
26. Gosset D, Guery M, Kryger B (1991) Thermal properties of some boron-rich compounds («BnC» and AlB_{12}). in *AIP Conference Proceedings (American Institute of Physics)* 380-383. [Link: https://bit.ly/2ORkC66](https://bit.ly/2ORkC66)
27. Wang C, Ling B, Zhang L, Cao ZX, Yang H, et al. (2014) Elementary research on preparation of AlB_{12} powder by self-propagating high-temperature synthesis (SHS). in *Materials Science Forum (Trans Tech Publ)* 773-74: 365-369. [Link: http://bit.ly/3s833bj](http://bit.ly/3s833bj)
28. Shiryayev A (1993) Distinctive features of thermodynamic analysis in SHS investigations. *Journal of engineering physics and thermophysics* 65: 957-962. [Link: https://bit.ly/3tl4cXx](https://bit.ly/3tl4cXx)
29. Munir Z (1992) Reaction synthesis processes: mechanisms and characteristics. *Metallurgical Transactions A* 23: 7-13. [Link: https://bit.ly/3seNz5t](https://bit.ly/3seNz5t)



30. Gennari S, Tamburini UA, Maglia F, Spinolo G, Munir ZA (2006) A new approach to the modeling of SHS reactions: Combustion synthesis of transition metal aluminides. Acta Materialia 54: 2343-2351. [Link: http://bit.ly/3f9KnUS](http://bit.ly/3f9KnUS)

31. Masoudian A, Karbasi M, SharifianJazi F, Saidi A (2013) Developing Al₂O₃-TiC in-situ nanocomposite by SHS and analyzing the effects of Al content and mechanical activation on microstructure. Journal of Ceramic Processing Research 14: 486-491. [Link: https://bit.ly/31m5ITb](https://bit.ly/31m5ITb)

Discover a bigger Impact and Visibility of your article publication with Peertechz Publications

Highlights

- ❖ Signatory publisher of ORCID
- ❖ Signatory Publisher of DORA (San Francisco Declaration on Research Assessment)
- ❖ Articles archived in worlds' renowned service providers such as Portico, CNKI, AGRIS, TDNet, Base (Bielefeld University Library), CrossRef, Scilit, J-Gate etc.
- ❖ Journals indexed in ICMJE, SHERPA/ROMEO, Google Scholar etc.
- ❖ OAI-PMH (Open Archives Initiative Protocol for Metadata Harvesting)
- ❖ Dedicated Editorial Board for every journal
- ❖ Accurate and rapid peer-review process
- ❖ Increased citations of published articles through promotions
- ❖ Reduced timeline for article publication

Submit your articles and experience a new surge in publication services
(<https://www.peertechz.com/submission>).

Peertechz journals wishes everlasting success in your every endeavours.

Copyright: © 2021 Wang C, et al. This is an open-access article distributed under the terms of the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original author and source are credited.

Citation: Wang C, Cao X, Dong M, Cao X, Xue X, et al. (2021) Theoretical calculation of self-propagating high-temperature synthesis (SHS) preparation of AlB₁₂. Ann Math Phys 4(1): 009-012. DOI: <https://dx.doi.org/10.17352/amp.000019>